Stainless Steel Electrodes

OK 61.50

A rutile based stainless steel electrode for SMAW of 18Cr-8Ni type steels

Classification AWS A5.4: E308-16

DESCRIPTION

OK 61.50 is an AC/DC rutile coated 20Cr-10Ni stainless steel electrode. The unique flux coating allows easy striking and restriking and is completely free from short-circuiting during welding.

APPROVALS: NPC, PDIL & TOYO

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Pro	
C Si Mn Cr Ni	0.05 0.80 0.75 20.50 9.10	YS (N/mm²) UTS (N/mm²) Elongation (%)	470 630 42

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying

OK 61.30

A rutile based extra low carbon stainless steel electrode for SMAW of 18Cr-8Ni type steels

Classification AWS A5.4: E308L-16

DESCRIPTION

OK 61.30 is a rutile based extra low carbon 20Cr-10-Ni type stainless steel electrode with a controlled ferrite that provides excellent resistance to corrosion, cracking and high temperature scaling resistance up to 800°C.

APPROVALS: PDIL & TOYO

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal		All Weld	
Composition (Wt.%)		Mechanical Properties	
C Si Mn Cr Ni	0.03 0.90 0.65 20.00 10.00	YS (N/mm²) UTS (N/mm²) Elongation (%)	540 620 42

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-90	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB 304B

A basic coated extra low carbon stainless steel electrode for SMAW of 18Cr-8Ni type steels

Classification AWS A5.4: E308L-15

DESCRIPTION

ESAB 304B is an extra low carbon, basic coated 19Cr-10Ni stainless steel electrode with outstanding welding properties in the vertical and overhead position. The weld metal is highly resistant to cracking and porosity and has good impact toughness at very low temperatures.

APPROVAL: NPC

WELDING CURRENT: DC+

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Properties	
C Si Mn	0.03 0.40 1.50	YS (N/mm²) UTS (N/mm²) Elongation (%)	450 570 40
Cr Ni	19.00 10.50	Impact (CVN) @ -196ºC (Joules)	30

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	180-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 61.80

A Nb stabilised stainless steel electrode for SMAW of 18Cr-8Ni & stabilized stainless steels

Classification AWS A5.4: E347-16

DESCRIPTION

OK 61.80 is a rutile type low carbon 19Cr-10Ni stabilized stainless steel electrode. Niobium minimizes the chromium carbide precipitation and thereby improves the intergranular corrosion resistance.

APPROVALS: NPC & TOYO

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Propertie	es
C 0.03 Si 0.90 Mn 0.65 Cr 19.8 Ni 9.80 Nb 0.65	30 30	YS (N/mm²) UTS (N/mm²) Elongation (%)	550 630 35

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



OK 63.50

A rutile based stainless steel electrode for SMAW of 18Cr-12Ni-2.5Mo type steels

Classification AWS A5.4: E316-16

DESCRIPTION

OK 63.50 is a rutile coated stainless steel electrode with a unique low moisture absorption coating depositing a weld metal of the type 18Cr-12Ni-2.5Mo.

APPROVALS: NPC, PDIL & TOYO

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Pro	=
Si 0 Mn 0 Cr 1! Ni 1:	.05 .70 .75 9.50 2.00 .10	YS (N/mm²) UTS (N/mm²) Elongation (%)	480 650 42

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 63.30

A rutile based extra low carbon stainless steel electrode for SMAW of 18Cr-12Ni-2.5Mo type steels

Classification AWS A5.4: E316L-16

DESCRIPTION

OK 63.30 is an extra low carbon, rutile based electrode depositing a weld metal of the type 18Cr-12Ni-2.5Mo. It is completely free from short-circuiting during welding coupled with excellent striking and restriking properties. It provides a self releasing slag and a weld bead that is extremely smooth and shiny.

APPROVALS: PDIL & TOYO

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

11010	Metal tion (Wt.%)	All Weld Mechanical Pro	
C Si Mn Cr Ni Mo	0.03 0.85 0.60 18.30 12.00 2.30	YS (N/mm²) UTS (N/mm²) Elongation (%)	500 590 40

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB 316KCR

An extra low carbon stainless steel electrode depositing ferrite free weld metal

Classification AWS A 5.4: E316L-16 (Nearest)

DESCRIPTION

ESAB 316KCR is a specially designed extra low carbon stainless steel electrode to deposit a ferrite free, fully austenitic weld metal with better corrosion resistance to hydrochloric, nitric and sulphuric acids.

APPROVALS: PDIL, SNAMPROGETTI (CR.UR.510 rev 03) & TOYO

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)	All Weld Mechanical Prop	erties
C 0.04 Si 0.40 Mn 1.20 Cr 18.00 Ni 14.20 Mo 2.20	YS (N/mm²) UTS (N/mm²) Elongation (%)	450 570 38

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-90	Weight Per Box: 10 Kgs
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 67.67

A rutile based stainless steel electrode for SMAW of similar composition steels & dissimilar steels

Classification AWS A 5.4: E309-16

DESCRIPTION

OK 67.67 is a rutile based, all positional electrode depositing a weld metal of the type 23Cr-13Ni. The weld deposit provides excellent resistance to corrosion and oxidation at very high temperatures, up to 1100°C.

APPROVALS: NPC, PDIL & TOYO
WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal		All Weld	
Composition (Wt.%)		Mechanical Properties	
C Si Mn Cr Ni	0.04 0.75 0.70 23.20 13.20	YS (N/mm²) UTS (N/mm²) Elongation (%)	480 590 36

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB 309

A basic coated stainless steel electrode for SMAW of similar composition steels & dissimilar steels

Classification AWS A 5.4: E309-15

DESCRIPTION

ESAB 309 is a basic coated, all positional electrode depositing a weld metal of the type 23Cr-13Ni. The weld deposit is extremely tough, resistant to corrosion and oxidation at elevated temperatures, up to 1100°C.

WELDING CURRENT: DC+

TYPICAL PROPERTIES

Weld Metal		All Weld	
Composition (Wt.%)		Mechanical Properties	
C Si Mn Cr Ni	0.05 0.70 0.80 23.80 13.20	YS (N/mm²) UTS (N/mm²) Elongation (%)	490 620 40

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 67.60

A rutile based extra low carbon 23Cr-13Ni stainless steel electrode for SMAW

Classification AWS A 5.4: E309L-16

DESCRIPTION

OK 67.60 is a rutile based, extra low carbon, all positional electrode of 23Cr-13Ni type for joining of stainless steels to unalloyed or low alloyed steels and for surfacing of unalloyed steels.

APPROVALS: NPC, PDIL & TOYO

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal		All Weld	
Composition (Wt.%)		Mechanical Properties	
C Si Mn Cr Ni	0.03 0.75 0.85 23.00 13.60	YS (N/mm²) UTS (N/mm²) Elongation (%)	490 600 42

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB 309LC

A basic coated extra low carbon 23Cr-13Ni stainless steel electrode for SMAW

Classification AWS A 5.4: E309L-15

DESCRIPTION

ESAB 309LC is an extra low carbon all positional basic coated electrode giving austenitic weld deposit of 23Cr-13Ni type. It is suitable for welding heat resistant Cr-Ni alloyed steels and stainless steels to unalloyed or low alloyed steels, where better toughness is required.

WELDING CURRENT: DC+

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Properties	
C Si Mn Cr Ni	0.03 0.75 1.00 23.50 13.70	YS (N/mm²) UTS (N/mm²) Elongation (%)	470 590 40

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 67.70

A rutile based 23Cr-13Ni-2.5Mo stainless steel electrode for SMAW

Classification AWS A 5.4: E309Mo-16

DESCRIPTION

OK 67.70 is a rutile based, over alloyed stainless steel electrode giving a weld deposit of 23Cr-13Ni-2.5Mo type, for welding stainless steels to other types of steels and for use as a buffer layer in welding acid resisting clad steels.

APPROVALS: NPC & PDIL

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

	Metal tion (Wt.%)	All Weld Mechanical Properties		
C Si Mn Cr Ni Mo	0.06 0.80 0.60 24.00 13.50 2.60	YS (N/mm²) UTS (N/mm²) Elongation (%)	530 630 32	

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB 309Mo

A basic coated 23Cr-13Ni-2.5Mo stainless steel electrode for SMAW

Classification AWS A 5.4: E309Mo-15

DESCRIPTION

ESAB 309Mo is a basic coated, over-alloyed stainless steel electrode giving a weld deposit of 23Cr-13Ni-2.5Mo type, for welding stainless steels to other types of steels, where better toughness is required.

WELDING CURRENT: DC+

TYPICAL PROPERTIES

Weld Metal		All Weld		
Composition (Wt.%)		Mechanical Properties		
C Si Mn Cr Ni Mo	0.06 0.80 0.80 24.00 13.00 2.50	YS (N/mm²) UTS (N/mm²) Elongation (%)	520 620 30	

CURRENT RANGE & PACKING DATA

Size	Length Current Range		Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

ESAB 309LMo

A basic coated extra low carbon stainless steel electrode for SMAW of similar composition steels & dissimilar steels

Classification AWS A 5.4: E309LMo-15

DESCRIPTION

ESAB 309LMo is an extra low carbon, basic coated all positional stainless steel electrode, giving an austenitic weld deposit of 23Cr-13Ni-2.5Mo type. The weld metal has excellent resistance to corrosion and oxidation at elevated temperatures up to 1100°C in continuous service, coupled with good strength and toughness.

WELDING CURRENT: DC+

TYPICAL PROPERTIES

Weld Metal		All Weld		
Composition (Wt.%)		Mechanical Properties		
C Si Mn Cr Ni Mo	0.03 0.70 0.70 23.50 13.50 2.50	YS (N/mm²) UTS (N/mm²) Elongation (%)	500 600 34	

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB 309Cb

A Nb stabilised stainless steel electrode for SMAW of similar composition steels & dissimilar steels

Classification AWS A 5.4: E309Nb-15

DESCRIPTION

ESAB 309Cb is a basic coated stainless steel electrode giving austenitic weld deposit of 23Cr-13Ni type. Columbium provides immunity against weld decay. The C-Nb ratio is carefully controlled to provide stabilization against intergranular corrosion.

WELDING CURRENT: DC+

TYPICAL PROPERTIES

	ld Metal sition (Wt.%)	All Weld Mechanical Pro	
C Si Mn Cr Ni Nb	0.04 0.80 1.00 23.50 13.50 0.70	YS (N/mm²) UTS (N/mm²) Elongation (%)	510 630 30

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in heat sealed plastic cartons and five of these cartons are shrink wrapped in a card board box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 67.13

A stainless steel electrode depositing fully austenitic weld metal for SMAW of 25Cr-20Ni type steels

Classification AWS A 5.4: E310-16

DESCRIPTION

OK 67.13 is a semi basic type austenitic stainless steel electrode depositing a 25Cr-20Ni type weld deposit, which has excellent stability and oxidation resistance in continuous service up to 1100°C.

APPROVALS: NPC

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Compositi		All Weld Mechanical Properties		
C Si Mn Cr Ni Mo	0.10 0.60 1.70 26.50 21.00 0.10	YS (N/mm²) UTS (N/mm²) Elongation (%)	430 600 34	

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB RSW

A rutile based high alloyed universal electrode for joining steels of unknown composition

Classification AWS A 5.4: E312-16

DESCRIPTION

ESAB RSW is a rutile coated all positional electrode, for welding of complex dissimilar alloys and high strength steels with low heat input, giving sound joints free from any cracks and fissures. It is a specially designed high alloy electrode for joining steels of unknown composition. The weld metal has high strength combined with excellent resistance against impact, heat (excellent scaling resistance up to 1150°C) and corrosion.

APPROVALS: CQA (Met), Ichapore & DGQA

WELDING CURRENT: DC+, AC 70 V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Properties		
C Si Mn Cr Ni	0.09 0.50 1.80 30.00 10.00	YS (N/mm²) UTS (N/mm²) Elongation (%)	600 770 23	
Мо	0.20			

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in cartons and four of these cartons are shrink wrapped in a cardboard box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 67.45

A 20Cr-10Ni-5Mn stainless steel electrode for SMAW

Classification AWS A 5.4: E307-16 (Nearest)

DESCRIPTION

OK 67.45 is an austenitic stainless steel electrode giving a weld metal of the 20Cr-10Ni-5Mn type. The tough weld metal imparts excellent crack resistance, when welding steels of even poor weldability.

APPROVALS: CQA (Met), Ichapore & DGQA

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal		All Weld		
Composition (Wt.%)		Mechanical Properties		
C Si Mn Cr Ni Mo	0.04 0.60 5.10 20.50 10.50 0.60	YS (N/mm²) UTS (N/mm²) Elongation (%)	450 610 45	

CURRENT RANGE & PACKING DATA

	Size	Length	Current Range	Packing
ı	(mm)	(mm)	(Amps)	
	2.50	350	60-100	Weight Per Box: 10 Kg
	3.15	350	80-120	Weight Per Carton
	4.00	350	120-170	(Packet): 2 Kg
	5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB CHROMWELD G

A rutile coated 18Cr-8Ni-4Mn stainless steel electrode for SMAW

DESCRIPTION

ESAB CHROMWELD G is a rutile coated stainless steel electrode depositing an 18Cr-8Ni-5Mn work hardening type weld metal. The electrode is specially designed for applications involving good work hardening properties and for joining of high tensile steels.

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Properties	
C Si Mn Cr Ni Mo	0.06 0.80 4.50 18.40 8.20 0.30	YS (N/mm²) UTS (N/mm²) Elongation (%)	470 630 38

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in cartons and four of these cartons are shrink wrapped in a cardboard box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

ESAB ARMOID 1

A special stainless steel electrode for SMAW of armour plates and crack sensitive steels

DESCRIPTION

ESAB ARMOID 1 is a stainless steel electrode designed for joining of high strength and dissimilar alloys, armour plates and other crack sensitive steels. It deposits an austenitic weld metal with sufficient residual ferrite to impart extreme crack resistivity.

APPROVALS: CQA (Met), Ichapore & DGQA

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Pro	
C Si Mn Cr Ni Mo	0.08 0.50 1.40 19.50 8.50 2.80	UTS (N/mm²) Elongation (%)	730 35

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	60-100	Weight Per Box: 10 Kg
3.15	350	80-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



OK 68.10

A basic coated stainless steel electrode depositing a ferritic 13Cr weld metal for SMAW

Classification AWS A5.4: E410-15

DESCRIPTION

OK 68.10 is a basic coated stainless steel electrode giving ferritic weld metal of 13Cr type for welding steels of similar composition.

WELDING CURRENT: DC+

TYPICAL PROPERTIES

Weld Metal		All Weld	
Composition (Wt.%)		Mechanical Properties	
C Si Mn Cr Ni	0.03 0.40 0.70 12.00 0.40	UTS (N/mm²) Elongation (%)	520 25

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	70-100	Weight Per Box: 10 Kg
3.15	350	90-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in cartons and four of these cartons are shrink wrapped in a cardboard box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 68.00

A rutile based stainless steel electrode for SMAW of 13Cr-4Ni-Mo type stainless steel castings

Classification AWS A 5.4: E410NiMo-16

DESCRIPTION

OK 68.00 is a specially designed rutile coated stainless steel electrode depositing 12Cr-4.5Ni-0.5 Mo weld metal. It has excellent welding characteristics in flat, H-V position and V-up positions.

WELDING CURRENT: DC+, AC 70V

TYPICAL PROPERTIES

Weld Metal Composition (Wt.	All We %) Mechanical P	
C 0.03 Si 0.35 Mn 0.90 Cr 12.00 Ni 4.70 Mo 0.60	UTS (N/mm²) Elongation (%)	800 15

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	70-100	Weight Per Box: 10 Kg
3.15	350	90-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5



ESAB 430

A basic coated stainless steel electrode depositing a ferritic 17Cr weld metal for SMAW

Classification AWS A 5.4: E430-15

DESCRIPTION

ESAB 430 is a basic coated stainless steel electrode giving ferritic weld metal of 17Cr type for welding steels of similar composition.

WELDING CURRENT: DC+

TYPICAL PROPERTIES

	l Metal tion (Wt.%)	All Weld Mechanical Pro	
C Si Mn Cr Ni	0.03 0.60 0.35 16.50 0.35	UTS (N/mm²) Elongation (%)	520 22

CURRENT RANGE & PACKING DATA

Size	Length	Current Range	Packing
(mm)	(mm)	(Amps)	
2.50	350	70-100	Weight Per Box: 10 Kg
3.15	350	90-120	Weight Per Carton
4.00	350	120-170	(Packet): 2 Kg
5.00	350	160-210	No. of Cartons (Packets) in a Box: 5

PACKING: Electrodes are packed in cartons and four of these cartons are shrink wrapped in a cardboard box. This electrode can also be made available in moisture resistant vacuum packed cartons, which can be used without redrying.

OK 67.50

A rutile based stainless steel electrode for SMAW of duplex stainless steels

Classification AWS A5.4: E2209-17

DESCRIPTION

OK 67.50 is an acid rutile electrode specially designed for welding of ferritic-austenitic stainless steels of the type UNS S31803 (popularly known as "Duplex stainless steels").

APPROVALS: ABS, BV, CE, CWB, DNV, Seproz & VdTÜV

WELDING CURRENT: DC+, AC 60V

TYPICAL PROPERTIES

-	Veld Metal position (Wt.	All Wo	
С	0.03	YS (N/mm²)	690
Si	0.75	UTS (N/mm²)	850
M	n 0.90	Elongation (%)	25
Cı	22.50	Impact (CVN)	
Ni	9.50	@ +20°C (Joules) 50
M	o 3.00	@ -30°C (Joules)	40
C	u 0.10		
N	0.15		

CURRENT RANGE

Size (mm)	Length (mm)	Current Range (Amps)
2.50	300	50-90
3.20	350	80-120
4.00	350	90-160
5.00	350	150-220

PACKING: Electrodes are packed in moisture resistant vacuum packed cartons, which can be used without redrying.



OK 68.55

A basic coated stainless steel electrode for SMAW of super duplex stainless steels

Classification AWS A5.4: E2594-15

DESCRIPTION

OK 68.55 is a basic coated electrode for welding austenitic-ferritic steels of the super duplex type. OK 68.55 deposits a weld metal with high ductility that has very high resistance to pitting, crevice and stress corrosion cracking.

APPROVALS: DNV

WELDING CURRENT: DC+

TYPICAL PROPERTIES

Weld Metal Composition (Wt.%)		All Weld Mechanical Properties	
С	0.04	YS (N/mm²)	700
Si	0.45	UTS (N/mm²)	900
Mn	0.80	Elongation (%)	28
Cr	25.20	Impact (CVN)	
Ni	9.70	@ -20°C (Joules)	70
Мо	4.00	@ -40°C (Joules)	55
N	0.25	@ -60ºC (Joules)	45

CURRENT RANGE

Size	Length	Current Range
(mm)	(mm)	(Amps)
2.50	300	50-80
3.20	350	60-100
4.00	350	100-140

PACKING: Electrodes are packed in moisture resistant vacuum packed cartons, which can be used without redrying.